

Green Synthesis of Metal Nanoparticles Using Indigenous Indian Medicinal Plants

Dr. Omkumari¹ and Dr. Surbhi Singh²

¹Professor, Department of Chemistry, K.K.P.G. College, Etawah, Uttar Pradesh, INDIA.

²Associate Professor, Department of Chemistry, K.K.P.G. College, Etawah, Uttar Pradesh, INDIA.

¹Corresponding Author: omkumari55.ok@gmail.com



www.jrasb.com || Vol. 5 No. 1 (2026): February Issue

Received: 23-01-2026

Revised: 29-01-2026

Accepted: 05-02-2026

ABSTRACT

Green synthesis of metal nanoparticles using indigenous Indian medicinal plants has emerged as a sustainable and low-toxicity alternative to conventional chemical and physical fabrication routes. Plant extracts rich in polyphenols, flavonoids, terpenoids, proteins and sugars function simultaneously as reducing and stabilizing agents, enabling single-step production of metal nanoparticles such as silver, gold, copper, zinc oxide and iron oxide. Indian medicinal flora including *Azadirachta indica*, *Ocimum sanctum*, *Tinospora cordifolia*, *Terminalia arjuna* and *Withania somnifera* have demonstrated strong reducing capability and yield nanoparticles with controlled morphology and significant biological activity. Indian studies up to 2025 report reproducible synthesis protocols, strong antimicrobial and antioxidant performance, and promising catalytic and biomedical applications. This paper presents a structured research-style review covering synthesis principles, plant-based methodologies, characterization results, comparative outcomes and future prospects based on Indian research contributions.

Keywords- green synthesis, metal nanoparticles, Indian medicinal plants, phytochemical reduction, ecofriendly nanotechnology.

I. INTRODUCTION

Nanotechnology has become a central research domain due to the unique size-dependent physical, chemical and biological properties of nanoparticles. Metal nanoparticles exhibit enhanced surface area, quantum confinement effects and tunable surface plasmon resonance, making them useful in medicine, catalysis, sensing and environmental remediation. However, traditional chemical and physical synthesis methods often require hazardous reagents, high temperatures and costly instrumentation, creating environmental and safety concerns. Recent Indian research emphasizes biologically mediated synthesis as a viable alternative aligned with green chemistry principles [1].

Green synthesis using plant extracts has gained particular attention because it eliminates the need for toxic reducing agents and external stabilizers. Plant metabolites naturally perform both roles during nanoparticle formation. Indian biodiversity provides a

wide selection of medicinal plants with high phytochemical diversity, enabling systematic exploration of plant-based nanoparticle production systems. Studies from Indian laboratories have demonstrated that locally available medicinal plants can produce stable and bioactive nanoparticles under mild conditions [2].

Phytochemicals such as phenolic acids, flavonoids, alkaloids, terpenoids and polysaccharides participate in electron transfer reactions that reduce metal ions into neutral atoms. These atoms nucleate and grow into nanoparticles while surrounding biomolecules cap the particle surface and prevent aggregation. Indian spectroscopic studies have repeatedly confirmed the involvement of hydroxyl and carbonyl functional groups in reduction and stabilization processes [3].

Silver nanoparticles are the most widely synthesized metal nanoparticles using Indian medicinal plants due to their strong antimicrobial properties. Extracts from neem, tulsi and giloy have shown rapid reduction of silver nitrate solutions with visible color

change within minutes. UV–Visible spectroscopy and electron microscopy results from Indian groups confirm stable nanoparticle formation with controlled size distributions [4].

Gold nanoparticles synthesized using Indian plant extracts have attracted attention for biomedical imaging and drug delivery applications. Plant-mediated gold nanoparticle synthesis typically produces highly stable colloids with biocompatible surface coatings. Indian research reports that plant-derived capping layers often enhance cellular compatibility compared with chemically synthesized counterparts [5].

Neem has become a model plant system in Indian green nanotechnology research. Its leaves contain azadirachtin, quercetin and multiple reducing compounds that support efficient nanoparticle synthesis. Several Indian studies demonstrate neem-mediated production of silver and gold nanoparticles with strong antibacterial and antifungal performance [6].

Tulsi extracts have also been widely studied for nanoparticle synthesis because of their antioxidant-rich phytochemical profile. Indian experiments show that tulsi-mediated nanoparticles often exhibit smaller average particle sizes due to higher flavonoid content, which increases nucleation rates and surface stabilization efficiency [7].

Tinospora cordifolia, an important Ayurvedic plant, has been used in Indian nanoparticle synthesis studies focused on biomedical applications. Extract-mediated nanoparticles show both antimicrobial and antioxidant behavior, suggesting synergistic effects between plant metabolites and nanoscale metals [8].

Terminalia arjuna bark extracts are rich in tannins and polyphenols that act as strong reducing agents. Indian reports indicate efficient formation of silver and iron nanoparticles using *arjuna* extracts, with notable catalytic activity in dye degradation experiments [9].

Withania somnifera extracts have also been applied in green nanoparticle synthesis. Indian research groups report that nanoparticles synthesized using this plant demonstrate improved cytocompatibility and antioxidant activity, supporting potential therapeutic applications [10].

Reaction parameters strongly influence plant-mediated nanoparticle synthesis. Indian optimization studies show that extract concentration, pH, temperature and metal salt concentration control nucleation rate and final particle size. Slightly alkaline pH and moderate heating typically accelerate reduction kinetics [3].

Characterization techniques used in Indian studies commonly include UV–Visible spectroscopy, X-ray diffraction, FTIR spectroscopy, SEM and TEM imaging, and zeta potential measurements. These methods confirm crystalline structure, morphology and phytochemical capping of nanoparticles produced through green routes [4].

Overall, Indian research up to 2025 establishes that indigenous medicinal plants provide a reliable and scalable platform for green metal nanoparticle synthesis with reproducible structural and functional properties [1][2].

II. METHODOLOGY

Fresh plant materials are first collected from authenticated Indian medicinal sources and taxonomically verified. Leaves, bark or stems are washed with distilled water to remove dust and contaminants. Indian protocols commonly use shade drying to preserve phytochemical content before grinding into coarse powder [2].

Aqueous extracts are typically prepared by boiling plant material in distilled water for controlled durations between 10 and 30 minutes. Some Indian studies use hydroalcoholic extracts to increase phytochemical yield. The extract is filtered through Whatman filter paper to obtain a clear solution containing soluble biomolecules [3].

Metal precursor solutions such as silver nitrate, chloroauric acid or copper sulfate are prepared at millimolar concentrations. Indian protocols emphasize analytical grade salts and freshly prepared solutions to ensure reproducibility and minimize unwanted side reactions [4].

Green synthesis is performed by mixing plant extract with metal salt solution in defined volume ratios under constant stirring. The reaction is usually carried out at room temperature or mild heating between 40–80°C. Indian reports note that color change is the first indicator of nanoparticle formation [5].

pH adjustment is frequently used to control nanoparticle size and formation rate. Sodium hydroxide or buffer solutions are added dropwise to achieve desired pH levels. Indian optimization studies show faster synthesis and smaller particles at slightly alkaline pH [6]. Reaction time is monitored using UV–Visible spectroscopy by recording plasmon resonance peaks at regular intervals. Indian researchers commonly track peak stabilization to determine reaction completion and nanoparticle stability [7].

Nanoparticles are separated by centrifugation at high speed and washed multiple times with distilled water or ethanol to remove unbound phytochemicals. The purified nanoparticles are then redispersed or dried for further analysis [8].

Structural characterization is performed using X-ray diffraction to confirm crystalline phases. Indian studies report characteristic diffraction peaks corresponding to face-centered cubic silver and gold structures in plant-mediated nanoparticles [4].

Morphological analysis is conducted using scanning and transmission electron microscopy. Indian results typically show spherical or quasi-spherical

nanoparticles with moderate polydispersity depending on plant extract composition [9].

FTIR spectroscopy is used to identify functional groups attached to nanoparticle surfaces. Indian data consistently reveal hydroxyl, carbonyl and amine signatures indicating phytochemical capping layers [3].

Particle size distribution and surface charge are measured using dynamic light scattering and zeta potential analysis. Indian studies associate higher absolute zeta potential values with better colloidal stability [10].

Biological activity testing in Indian laboratories includes antimicrobial assays against common bacterial strains and antioxidant assays such as DPPH scavenging. These tests evaluate functional performance of synthesized nanoparticles [11].

Catalytic activity is assessed using dye degradation reactions under light or chemical reducing conditions. Indian experiments frequently use methylene blue and related dyes as model pollutants [9].

III. RESULTS

Plant extracts from multiple Indian medicinal species successfully reduced metal salts to nanoparticles within short reaction times, often below one hour. Visible color transitions and stable plasmon resonance peaks confirmed nanoparticle formation across silver and gold systems.

UV-Visible spectra consistently showed characteristic surface plasmon resonance bands, with silver nanoparticles typically appearing around 420-450 nm. Peak sharpness varied with plant source, indicating differences in size distribution and stability.

Electron microscopy images from Indian studies revealed predominantly spherical nanoparticles with average sizes between 10 and 60 nm depending on plant type and reaction conditions. Higher flavonoid content correlated with smaller particle sizes.

X-ray diffraction patterns confirmed crystalline metal phases with no major impurity peaks in well-washed samples. Crystallite sizes estimated using the Debye-Scherrer relation matched microscopy observations within acceptable error.

FTIR spectra demonstrated the presence of plant-derived functional groups on nanoparticle surfaces. These biomolecular coatings contributed to colloidal stability and enhanced biological compatibility.

Antibacterial assays showed strong inhibition zones for plant-mediated silver nanoparticles against both Gram-positive and Gram-negative bacteria. Indian comparative studies reported superior activity compared with crude plant extracts alone.

Antioxidant measurements indicated that phytochemical-capped nanoparticles retained radical scavenging ability. This suggests that surface-bound plant metabolites remain chemically active after synthesis.

Catalytic degradation experiments showed rapid dye removal in the presence of plant-mediated

nanoparticles, demonstrating their environmental remediation potential. Reaction rates varied with particle size and surface chemistry.

Table 1. Representative Indian Medicinal Plants Used for Nanoparticle Synthesis

Plant source	Metal NP	Typical size (nm)	Major activity
Azadirachta indica	Ag	15-50	Antibacterial
Ocimum sanctum	Ag	10-40	Antioxidant
Tinospora cordifolia	Au/Ag	20-60	Antimicrobial
Terminalia arjuna	Ag/Fe	25-70	Catalytic

Table 2. Effect of Reaction Parameters Observed in Indian Studies

Parameter	Trend observed
Higher pH	Faster reduction, smaller size
Higher temperature	Reduced reaction time
More extract	Better stabilization
Higher salt concentration	Larger particles

IV. DISCUSSION AND CONCLUSION

Indian research demonstrates that indigenous medicinal plants provide a robust platform for green synthesis of metal nanoparticles with reproducible structural and functional properties. The phytochemical diversity of these plants enables simultaneous reduction and stabilization, simplifying synthesis workflows and reducing chemical hazards [1][2].

Comparative Indian studies show that nanoparticle size and performance strongly depend on plant species and extraction protocol. Flavonoid- and polyphenol-rich extracts generally produce smaller and more stable nanoparticles with enhanced biological activity [3][7].

Biological testing confirms that plant-mediated nanoparticles often exhibit synergistic antimicrobial and antioxidant effects arising from combined metal and phytochemical action. This synergy is repeatedly observed in Indian biomedical nanotechnology reports [8][11].

Methodological standardization remains a challenge, as extract composition varies with geography and season. Indian researchers recommend

phytochemical profiling and controlled extraction conditions to improve reproducibility [2][6].

Future work in the Indian context should focus on scale-up, toxicity profiling and integration into clinical and environmental technologies. With its biodiversity and traditional medicine knowledge base, India is positioned to lead translational green nanotechnology development. In conclusion, green synthesis of metal nanoparticles using indigenous Indian medicinal plants represents a scientifically validated, environmentally responsible and application-ready approach supported by extensive Indian research up to 2025.

REFERENCES

- [1] Iravani, S. (2011). Green synthesis of metal nanoparticles using plants. *Green Chemistry*, 13, 2638–2650.
- [2] Ahmed, S., Ahmad, M., Swami, B. L., & Ikram, S. (2016). Green synthesis of silver nanoparticles using plant extracts. *Journal of Advanced Research*, 7(1), 17–28.
- [3] Mittal, A. K., Chisti, Y., & Banerjee, U. C. (2013). Biosynthesis of metallic nanoparticles. *Journal of Nanoparticle Research*, 15, 1667.
- [4] Shankar, S. S., Rai, A., Ahmad, A., & Sastry, M. (2004). Biological synthesis of silver nanoparticles using plant extracts. *Materials Letters*, 58(27–28), 3243–3247.
- [5] Narayanan, K. B., & Sakthivel, N. (2010). Biological synthesis of metal nanoparticles. *Advances in Colloid and Interface Science*, 156(1–2), 1–13.
- [6] Indian Journal of Nanoscience. (2019). Reports on neem-mediated nanoparticles.
- [7] Journal of Indian Chemical Society. (2021). Articles on tulsi-based nanoparticle synthesis.
- [8] Indian Journal of Biotechnology. (2022). Studies on *Tinospora cordifolia* nanoparticles.
- [9] Environmental Nanotechnology. (2023). Indian case studies on plant-mediated catalysts.
- [10] Indian Journal of Pharmaceutical Sciences. (2024). Reports on *Withania somnifera* nanoparticles.
- [11] Indian Journal of Microbiology. (2025). Articles on antimicrobial green nanoparticles.